

IDEAL (VS) LTD SUITE-151, 100 RYDERS LANE, PEOPLES PLAZA, MILLTOWN NEW JERSEY - 08850, U.S.A

TEL: 732-246-0337 FAX: 732-246-0523

PRODUCT DESCRIPTION	ALUMINUM FOIL IS COATED ON ONE SIDE WITH AN AGGRESSIVE SOLVENT BASED ACRY ADHESIVE. THE ADHESIVE IS PROTECTED BY A TOUGH KRAFT RELEASE LINER.			
TEST THICKNESS FOIL ADHESIVE RELEASE LINER TOTAL	TYPICAL VALUES (NOT FOR SPECIFICAT METRIC MILLIMETERS 0.03 0.04 0.06 0.14		TEST METHOD PSTC-33 ASTM-645 TAPPI-T-411-M-44	
TENSILE ELONGATION	METRIC NEWTON: PER METER 18 3%	S		TM-D-882-61T TM-D-882-61T
ADHESION, 180° PEEL SUBSTRATE: STAINLESS STEEL (APPLIED ONE MINUTE)	0.05 MM POLYEST METRIC NEWTON: PER METER 1796			TC-3 TM-D-3330
TACK, LOOP	METRIC NEWTON: PER METER 525	S	TM	-7A
SHEAR, STATIC	AREA 1.6 CM ² 6.5 CM ²	<u>LOAD</u> 1 KG 2.5 KG	<u>AVERAGE VALU</u> (<u>MINUTES</u>) > 10,000 > 10,000	<u>JE</u> PSTC 7, FEDERAL TEST, METHOD 147B
APPLICATIONS	USED FOR SEALING JOINTS AND SEAMS AGAINST MOISTURE AND VAPOR ON FOIL JACKETING INSULATION.			
SURFACE PREPARATION	IT IS ESSENTIAL, AS WITH ALL PRESSURE SENSITIVE TAPES, THAT THE SURFACE TO WHICH THE TAPE IS APPLIED BE CLEAN, DRY AND FREE OF GREASE AND OIL USE HEAT IF THE TEMPERATURE IS BELOW 50°F (10°C). SQUEEGEE TAPE FLAT.			
STORAGE & SHELF LIFE	ONE YEAR WHEN STORED AT 21°C/50% RELATIVE HUMIDITY OUT OF DIRECT SUNLIGHT.			
FEATURES AND BENEFITS (FIELD PROVEN)	FEATURES * SOFT TEMPER * EXCELLENT AI QUICK STICK * MANUFACTUR CLASS 1723S		* STRONG BOND SUBSTRATES	Y PRICED, GENERAL
COMPOSITION	FOIL : 0.03 MM SOFT TEMPER ALUMINUM FOIL. ADHESIVE : 0.04 MM SOLVENT BASED ACRYLIC ADHESIVE. RELEASE LINER : 65G/M² DENSIFIED KRAFT RELEASE LINER.			