

**INCREASED  
PRODUCTIVITY**

# TOP 1 - TOP 2

## INTERIOR SURFACE FILLER SYSTEM - PASTE

### TOP 1

- ▶ LEVELS IN ONE COAT UP TO 3 MM/COAT
- ▶ IMPROVED FILLING PROPERTIES
- ▶ READY-MIXED

### TOP 2

- ▶ EXTRA FINE AND WHITE
- ▶ VERY LOW PAINT ABSORPTION
- ▶ READY-MIXED



### PURPOSE

Surface filler system in paste, interior use, manual application.

### SUBSTRATES

**TOP 1 – TOP 2** can be applied on:

- Cement plastering
- Plaster boards
- Primed wood
- Concrete,
- Old painted surfaces

### OVERCOATING

**TOP 1 – TOP 2** can be painted over will all conventional types of paints (as well as epoxy and polyurethane) or covered with wall paper.

### Physical and technical FEATURES

**TOP 1 – TOP2:** fillers in paste form for interior use, made of selected quarry materials and resins.

- Characterization (NFT 36-005): Family III-Class 2
- Codification (EN 16566): G<sub>3</sub>S<sub>1</sub>V<sub>0</sub>W<sub>0</sub>A<sub>0</sub>C<sub>0</sub>R<sub>0</sub>
- Application thickness: TOP 1: up to 3 mm  
TOP 2: Up to 1 mm
- Consumption (in thin layer): TOP 1: 250 to 300 g/m<sup>2</sup>  
TOP 2: 200 to 250 g/m<sup>2</sup>
- Second coat: once the filler is dry
- Overcoat: When fully dry
- Colour: White
- Adhesion filler/substrate (EN 16566): > 0.5 Mpa

### USE AND STORAGE CONDITIONS

- Application tool : With smoothing or surfacing blade
- Tools cleaning: with water
- Preservation: product guaranteed 12 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from frost and sun.

### PACKAGING

- TOP 1: Bucket of 25 Kg
- TOP 2: Tub of 1,5 kg  
Buckets of 5 and 25 kg

### RECOMMENDATIONS and care for use

- Do not apply under a temperature < 8 °C and > 35 °C nor under an hygrometry rate over 70%.
- Do not apply on overheated surfaces
- Do not apply on damp substrates
- Do not apply on polystyrene, nor on wall paper, nor on exterior substrates.

### SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

### NORMATIVE DOCUMENTS to be referred to

- EN 16566: Coating Fillers for interior and/or exterior works.
- NFT 36-005: Characterization of paint products.
- DTU 59.1 (NFP 74-201): Building paint works.
- DTU 59.4 (NFP 74-204): wall papers and wall coverings processing

### HEALTH AND SAFETY

- No danger tag.
- Very low VOC emissions : < 0,01 %.
- Safety data sheets available on [www.toupretpro.co.uk](http://www.toupretpro.co.uk) or [toupret.com](http://toupret.com).

The data sheet information, especially the guidelines relevant to the application and final use of **TOP 1 - TOP 2** are provided in good faith and result from the knowledge of the products and experience of TOUPRET Company.  
The product is required to be used as per the trade practices rules book and in reference to our recommendations.  
The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.  
The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions



Information on the level of emission of volatile substances in indoor air, presenting a risk of inhalation toxicity, on a class scale from A + (very low emissions) to C (high emissions).