

[HIGH
QUALITY
FINISH]

INTERIOR FILLER LE REBOUCHEUR CRACK FILLER

- ▶ FAST SETTING : 30 MIN
- ▶ NO THICKNESS LIMITATION
- ▶ CAN BE SCREWED AND DRILLED
- ▶ ADHERES ON PAINTED SURFACES
- ▶ WHITE AND FINE

PURPOSE

Filler in powder, for interior use, manual application.

SUBSTRATES

LE REBOUCHEUR applies on either new or renovated substrates, either unpainted or painted:

- Gypsum plaster, plaster tiles, plasterboards,
- Old painted surfaces,
- Cement, concrete, cellular concrete, breeze blocks, bricks, stones.

OVERCOATING

LE REBOUCHEUR can be overcoated by any **TOUPRET** filler, any conventional paint or wall covering.

Physical and technical FEATURES

LE REBOUCHEUR: filler in powder form, made of gypsum plaster, selected quarry materials and cellulosic binder.

- Characterization (NFT 36-005): Family III class 3
- Codification (EN 16566): $G_3S_2V_0W_0A_0C_0R_0$
- Mixing rate: 50% water (hence 0.5 litre water per 1 kg powder)
- Application thickness: no thickness limitation
- Consumption: 1 kg powder allows to fill a volume of 1.1 litre
- Working time: 30 to 40 minutes
- Second coat: once the filler is dry
- Overcoating: 12 to 24 h average time (when fully dry)
- Colour: white
- Shore hardness: 80
- Adhesion filler/substrate (EN 16566): > 0,5 MPa

USE AND STORAGE CONDITIONS

- Application tool: filling knife or with trowel or blade
- Tools cleaning : with water.
- Preservation: product guaranteed 12 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from humidity.

PACKAGING

- Box: 1 kg.
- Bag: 5 kg.



RECOMMENDATIONS and care for use

- Do not apply on polystyrene, nor on adhesive coverings nor on exterior substrates.
- Do not apply under a temperature < 8 °C and > 35 °C nor under an hygrometry rate over 70%.
- Do not apply on warm/overheated surfaces
- Do not apply on damp surfaces
- Do not mix the paste any longer once it has begun to set.

SUBSTRATES PREPARATION

- Substrates to be prepared as per the current building trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS to be referred to

- EN 16566: Coating fillers for interior works and/or exterior .
- NFT 36-005: Characterization of paint products.
- French DTU 59.1 (NFP 74-201): Building paint works.
- French DTU 59.4 (NFP 74-204): Setting up of wall papers and wall coatings.

HEALTH AND SAFETY

- No danger tag.
- Very low VOC emissions : < 0,015 %.
- Safety data sheets available on www.toupretpro.co.uk or toupret.com.

The data sheet information, especially the guidelines relevant to the application and final use of **LE REBOUCHEUR** are provided in good faith and result from the knowledge of the products and experience of **TOUPRET** company.

The product is required to be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions.



Information on the level of emission of volatile substances in indoor air, presenting a risk of inhalation toxicity, on a class scale from A+ (very low emissions) to C (high emissions).