



**[ ONE COAT  
FILL ]**

# REDLITE

## FAST DRYING LIGHTWEIGHT FILLER



- ▶ **FILL IN ONE COAT**
- ▶ **CAN BE PAINTED IN 30 MINS**
- ▶ **WILL NOT SHRINK**
- ▶ **NO SANDING REQUIRED**

### PURPOSE

Ready to use lightweight filler, interior use, manual application.

### SUBSTRATES

**REDLITE** can be applied on any substrate either unpainted or painted

- Gypsum plaster, plaster tiles, plasterboards
- Old painted surfaces
- Cement, concrete, cellular concrete
- Breeze blocks, bricks, stones
- Primed wood

### OVERCOATING

**REDLITE** can be coated by any type of Toupret fillers, all types of paints and wall coverings.

### Physical and technical FEATURES

**REDLITE:** Interior filler in paste form made of lightweight material extracts and acrylic polymer.

- Characterization (NFT 36-005): Family III – Class 2
- Codification (EN 16 566): G<sub>3</sub>S<sub>1</sub>V<sub>0</sub>W<sub>0</sub>A<sub>0</sub>C<sub>0</sub>R<sub>0</sub>
- Application thickness: No limit
- Overcoating: 30 minutes (for 1 mm thickness) to 2 hours average time
- Colour: extra white
- Adhesion filler/substrate (EN 16 566): > 0.5 Mpa

### USE AND STORAGE CONDITIONS

- Tools: coating knife, smoothing blade or trowel
- Tools cleaning: with water
- Preservation: product guaranteed 12 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from frost

### PACKAGING

- Tub of 1 L
- Bucket of 4 L

### RECOMMENDATIONS and care for use

- Do not apply: under a temperature below +8°C nor above 35°C nor under a hygrometry rate above 70%.
- Do not apply on warm substrates.
- Do not apply on damp substrates.
- Do not apply on polystyrene nor on wall paper nor on exterior substrates.

### SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

### NORMATIVE DOCUMENTS to be referred to

- EN 16566: Coating Fillers for interior and/or exterior works.
- NFT 36-005: Characterization of paint products.
- DTU 59.1 (NFP 74-201): Building paint works.
- DTU 59.4 (NFP 74-204) : Wall papers and wall coatings works.

### HEALTH AND SAFETY

- No danger tag.
- Very low VOC emissions : <0,25%
- Safety data sheets available on [www.toupretpro.co.uk](http://www.toupretpro.co.uk) or [toupret.com](http://toupret.com).

The data sheet information, especially the guidelines relevant to the application and final use of **REDLITE** are provided in good faith and result from the knowledge of the products and experience of TOUPRET Company.

The product is required to be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions



Information on the level of emission of volatile substances in indoor air, presenting a risk of inhalation toxicity, on a class scale from A+ (very low emissions) to C (high emissions).